





FICHA TÉCNICA

PAVIMENTO COMPÓSITO SPC

15x 
 = 3,3306m²
 = 27,70 Kg

50x 
 = 166,53m²

1 Dimensions & Assembly inspection

Inspection Items	Standard	Sample Size	Inspection records	Determination
Length	1220±1mm	20pcs	1220	PASS
Width	182±0.15mm	20pcs	181.93-182.06	PASS
Thickness	3,5±0.20mm	20pcs	3.47-3.54	PASS
High Difference	Ha ≤ 0.10mm / Hmax ≤ 0.15mm	8pcs	PASS	PASS
Gaps	Oa ≤ 0.10mm / Omax ≤ 0.15mm	8Pcs	PASS	PASS

2 Appearance inspections

Inspection Items	Standard	Sample Size	Inspection records	Determination
Color Match	Match with customer sample	20pcs	NA	NA
	Match with last Batch	20pcs	PASS	PASS
Embossing	Match with customer sample	20pcs	NA	NA
Gloss	6-8 degree	20pcs	6.5-8	PASS
Visual Defects	According to Defects sample	125pcs	NA	PASS

3 Packaging inspections

Inspection Items	Standard	Sample Size	Inspection records	Determination
Palletization	According to Order request	5pcs	PASS	PASS
Wood Pallets	According to Order request	5pcs	PASS	PASS
Carton & Label	According to Order request	20pcs	PASS	PASS
inserts	According to Order request	5pcs	NA	NA

4 Lab tests

Inspection Items	Standard	Sample Size	Inspection records	Determination
Abrasion	≥ 1800 Cycles(0.3mm Wear Layer) ≥ 4000Cycles(0.5mm Wear Layer)	1pcs	≥ 2000	PASS
Density	1.95-2.15 g/CM ³	3pcs	2.08	PASS
Dimension Stability	Ave ≤ 0.10% / Max ≤ 0.15%	3pcs	Ave=0.08%	PASS
Hardness	≥ 65 HD	3pcs	74	PASS
Peel Resistance	≥ 50N/50mm	3pcs	68	PASS

Final Determination	PASS
----------------------------	-------------